

TimberClear Top Coat

Clear Sealer For Fireshield® TimberClear Basecoat.

PRODUCT INFORMATION

DESCRIPTION

Fireshield® TimberClear Top Coat Matt & Semi Gloss is the second coat of the TimberClear fire rated system for interior timber surfaces. It is a clear, single pack solvent top coat sealer, designed for use over the Fireshield® TimberClear intumescent basecoat .

Fireshield TimberClear Top Coat is available in two gloss levels:

1. Matt (7 GU at 60°)
2. Semi Gloss (20 GU at 60°)

RECOMMENDED USE

- Fireshield® TimberClear Top Coat provides a sealing coat to protect the TimberClear basecoat.
- Fireshield® TimberClear Top Coat is an industrial product and can only be applied by Fireshield® Registered Applicators.
- The Fireshield® TimberClear system provides a certified Group 1-S fire rated surface finish.

Sequence of required coatings for interior zone installation (standard):

1. Fireshield® TimberClear basecoat.
2. Fireshield® TimberClear Top Coat Matt or Semi Gloss.

Contact Fireshield® prior to specification and installation where constant relative humidity is over 75% .

Maximum film thickness

At 23°C and 50% relative humidity, the minimum 70µm wet film thickness required will be achieved in one coat with an airless spray unit.

NOTE: Fireshield® TimberClear Top Coat Matt or Semi Gloss is designed to seal and protect the Fireshield® TimberClear intumescent basecoat from impact and moisture. Ensure a full and uniform coat is applied to a minimum 70µm wet film thickness to the entire area.

TOPCOATS

Fireshield® TimberClear Top Coat is not compatible with any other top coat. Any approved stain used with the system must be applied directly to the timber surface.

LIMITATIONS

- Can only be used in conjunction with the Fireshield® TimberClear basecoat.
- For interior use only in dry areas with <75% constant relative humidity.
- Do not use in external applications!

SHELF LIFE

Minimum 12-months when stored in conditions listed on this technical datasheet in original sealed containers, product is subject to re-inspection thereafter as shelf life is not an expiry date.

TECHNICAL INFORMATION

Specific gravity	1.05 + 1%
Non-volatile content	44%
Flash point	20°C
Colour	Clear
Packaging	5 litre.
Mixing	Thorough mechanical stir.
Thinning	Thin maximum 10%, increase WFT accordingly.
Clean up	Fireshield® Top Coat Thinner

COATING THICKNESS

Minimum WFT	> 70 microns WFT
Minimum DFT	> 30 microns DFT
Minimum grams/m ²	> 70 grams/m ²

DRYING TIMES

The following drying times have been measured with a wet film thickness of 70µm:

At a minimum air temperature of 23°C and relative air humidity of 50% the following drying times are applicable:

- 2 hours touch dry and
- 8 hours minimum to handle.

NOTE: Dry times may be lengthened by poor air flow and environmental conditions differing from those listed above, which are a guide only. Contact Fireshield® for more information.

Application should not take place in conditions which are deteriorating, e.g. the temperature is falling or there is a risk of condensation forming.

STORAGE CONDITIONS

Recommended storage conditions:

- Store at a temperatures above +5°C and below +35°C
- Store indoors and undercover in temperate conditions.
- Store away from direct sunlight, do not expose to extreme heat.
- Do not allow to freeze.
- Keep containers closed when not in use.
- Keep out of reach of children!

WARRANTY

12-month manufacturers shelf life warranty applies to product within the shelf life period.

APPLICATION NOTES

The product must be applied in strict accordance with the Fireshield application instructions. In particular the Applicator should ensure:

- The surface to be coated is completely clean and dry. Remove all dust, oil, grease, loose material or other contaminants .
- The product is occasionally stirred while using.
- Application occurs using suitable equipment for the substrate, working conditions and desired finish.
- Fill out Daily Record Sheets and PS3/Statement of Construction for compliance sign off at the conclusion of coating process.

PRECAUTIONS

The following precautions must be taken:

- Read the Fireshield® TimberClear Top Coat Material Safety Data Sheet (MSDS) before application and have a copy available on site at all times.
- Pay particular attention to Hazard Statements and PPOE requirements and avoid inhaling vapours when handling. Avoid contact with skin and eyes and ensure adequate ventilation.
- Read the Fireshield® Timber Application Guide in full before application.
- All work involving the application and use of this product should be compliant with all relevant National Health, Work Safety & Environmental standards and regulations.
- Where conditions may require variation from the recommendations on this Product Technical Data Sheet contact Fireshield® for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Fireshield®.

APPLICATION ENVIRONMENT

During application and drying, day or night ensure that:

- The air temperature is above +10°C and below +35°C.
- The relative air humidity level is below 75%.
- The area is well ventilated with constant air flow.

During application or drying protect from wetting/moisture/condensation and human impact. Electric heaters and dehumidifiers can also be used to help control the environmental conditions if necessary.

APPLICATION METHOD

Airless Spray

Airless spray is the recommended method of application and gives the best result.

Airless Equipment Recommendations

Pump flow rate	5 litres per minute e.g. Wagner/Graco Mk V
Hose Diameter	Dedicated hoses not below 3/8"
Spray Tip	Orifice size range of 412 to 413 tip size. Choose appropriate fan width depending upon substrate) to be coated 30° - 60°
Atomising Pressure	1,885 - 2610 psi

Brush

Brush application only suitable for small areas or touch-up and may result in a textured finish. Care must be taken to achieve the required specified dry film thickness. Typically, 100-300µm can be achieved per coat.

Roller

Roller application not advised, if used only suitable for small areas or touch-up and may result in a textured finish. Care must be taken to achieve the required specified dry film thickness. Typically, 100-300µm can be achieved per coat.

MAINTENANCE

The system has the ability to resist minor contact with moisture, impact and abrasion however, excessive wear or moisture contact may damage the system and if so, require inspection and possible remediation. A copy of the Maintenance Guide is available from Fireshield.

COMPLIANCE

NEW ZEALAND: Tested to EN13501-1:2018 and achieves Fire Class B-s1-d0. This is recognised as equivalent to Group 1-S under the NZBC Clause 3.4(a) providing compliance with NZBC C/AS1-C/AS7

AUSTRALIA: Codemark Certificate of Conformity CM-30071 providing Group 1 surface rating and compliance with the NCC 2022 CP14 for Class 2-9 Buildings. See the Codemark certificate for all conditions relating to a compliant application and installation.

SUPPLIER : FIRESHIELD

New Zealand
825 Colombo Street
Christchurch 8013,
New Zealand
Ph: 0800 347 374
www.fireshieldcoatings.com

Australia
13 North Concourse, Beaumaris,
Victoria 3193
ABN: 95 336 533 948
Ph: 1-800 092 097



It is the user's responsibility to check that you have the latest technical datasheet available by visiting fireshieldcoatings.com or checking with your local Fireshield Representative as the information contained in this technical data sheet is modified from time to time in line with our policy of continuous product development. The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) are correct to the best of our knowledge. Fireshield has no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. Fireshield hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. You should request a copy of this document and review it carefully.